<u>DESCRIPTION</u>

Double Coated Crepe Paper on both sides with a synthetic rubber based adhesive. A high quality saturated crepe paper coated on both sides with a ultra high tack and moderate shear properties. Supplied on a 60# silicone treated release paper. Custom slit to width

APPLICATION PROCESS

Economical, general purpose double coated tape designed for applications where good tensile strength is needed. Applications include general purpose bonding of papers, films and fabrics; splicing and core start up applications; and mounting golf club grip handles depending on lubricant type. Its special adhesive formulation makes this tape excellent for holding wood cuts and dies with little to no residue upon removal.

MATERIAL DESCRIPTION	
SIZE (width x length)	36 yd
COLOR	White
ADHESIVE TYPE	Pressure-Sensitive Tape
CONSTRUCTION	Double Sided
SELF WOUND	No
RELEASE LINER MATERIAL	Siliconized Paper
RELEASE LINER THICKNESS	
WEIGHT	

TECHNICAL DATA	
ADHESIVE LAYER	Rubber
BACKING/CARRIER MATERIAL	Paper
BACKING/ADHESIVE THICKNESS	4.5 mil
TOTAL THICKNESS	6.0 mils
ADHESION TO STEEL	80 oz/in
TENSILE STRENGTH	16 lbs/in width
ELONGATION	5% at break
TEMPERATURE APPLICATION	
TEMPERATURE OPERATING	30°F to 150°F

Physical and perfomance characteristics shown are obtained from tests recommended by vendor. Quality Assurance and Technical Service Departments do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

Surfaces to be bonded to should be dry, clean and free from oil and grease.

Typical shelf life is one (1) year from date of manufacture (DOM). Recommended storage conditions: 40-60% Humidity, 60°F to 80°F

Note: The information listed above has been obtained from controlled laboratory tests and is reliable, but should not be used for the purpose of writing specifications. It is offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. It is recommended that the prospective user determine the product suitability before adapting for commercial use.



