<u>DESCRIPTION</u>

Kraft Flatback Tape. A moisture resistant kraft flatback paper tape with an aggressive, pressure-sensitive natural/synthetic rubber adhesive. Desinged to offer a positive, attractive seal and excellent adhesion to minimize carton sealing failures and prevent pilferage. Cpmsodered bu ,amu as tje omdistru stamdard. Excellent balance of machine and cross direction tensile and tear strength. Remains strong under moist conditions. Custom slit to width

APPLICATION PROCESS

Offers strength, extensibility, conformability, and high cross direction tensile for general purpose applications. Carton sealing, packaging, silk screening, picture framing, beaming/leasing, splicing, and tabbing. Approved as packaging tape by both U.S. Postal Service and U.P.S (United Parcel Service).

| MATERIAL DESCRIPTION | |
|-------------------------|-------------------------|
| SIZE (width x length) | 59" X 1200 yd |
| COLOR | Brown Kraft |
| ADHESIVE TYPE | Pressure-Sensitive Tape |
| CONSTRUCTION | Single Coated |
| SELF WOUND | Yes |
| RELEASE LINER MATERIAL | N/A |
| RELEASE LINER THICKNESS | |
| WEIGHT | |
| | |

| TECHNICAL DATA | |
|----------------------------|-------------------------|
| ADHESIVE LAYER | Rubber |
| BACKING/CARRIER MATERIAL | Kraft Flatback Paper |
| BACKING/ADHESIVE THICKNESS | |
| TOTAL THICKNESS | 7.2 mil PSTC-133 |
| ADHESION TO STEEL | 50 oz/in width PSTC-101 |
| TENSILE STRENGTH | 40 lb/in width PSTC-131 |
| ELONGATION | 7% at break |
| TEMPERATURE APPLICATION | 50°F to 120°F |
| TEMPERATURE OPERATING | 32°F to 180°F |

Physical and performance characteristics shown are obtained from tests recommended by vendor. Quality Assurance and Technical Service Departments do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

Surfaces to be bonded to should be dry, clean and free from oil and grease.

Typical shelf life is one (1) year from date of manufacture (DOM). Recommended storage conditions: 40-60% Humidity, 60°F to 80°F

Note: The information listed above has been obtained from controlled laboratory tests and is reliable, but should not be used for the purpose of writing specifications. It is offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. It is recommended that the prospective user determine the product suitability before adapting for commercial use.



