



Shirley, MA 01464 Tel: 978 425 6761 Toll Free: 800 543 1324 (USA) Fax: 978 425 2278

Fax: 978 425 2278 www.bemisworldwide.com

Adhesives, Coatings, Specialty Films, Seam Tape

				Produ	ct:	4220				Versio		
										Date:	8/16/2004	ţ
	✓	Nylon		Polyester		Polyolefin		Polyure	thane	Vinyl		
•	cotton, ra	ayon, wo	noplastic polyamide adhesive film exhibits excellent adhesion to acetates, acrylics, silks yon, wool and most fabric substrates. 4220 adhesive film exhibits excellent washability ang resistance. 4220 can be steam activated.									
Adheres To:		Acetate	Acetates, Wool, Silk, Polycotton, Rayon.									
Composition:	Polyar	Polyamide										
Color:	Clear	Clear										
Weight:	22 gn	22 gm/m² per mil										
Substrate:		Releas	Release Paper, Stripped					Free Film = Manufactured as free film Stripped = Manufactured on RL but can be stripped.				
Nominal Thickness:		.003",	.003", .005", .007"									
Hardness:		90 A	90 A									
Softening Point:		116°C	116°C, 241°F TMA onset Temperature									
Melt Flow Index:		35 dg/	35 dg/minute					ition:	175°C	/ 2.16 Kg l	-oad	
Service Temperature:		NA	NA									
Washability:		Excellent										
Dry Cleaning Re	e:	: Excellent										

Comments:

^{*} Film samples were dried at 65C for 24 hours before testing was performed.